

brilliant

Bathroom Edition: Shower Wall Installation CME-2011 GECA 28-2006 v2 **Furniture and Fittings**



Reduce the cutting depth to allow the blade to cut approximately 7mm through the Akril, preferably cutting into a sacrificial MDF board or similar.

CIRCULAR BLADE GEOMETRY AND CONDITIONS

Circular Blades for Akril.

ger

Akril is best cut using fine-tooth Aluminum circular blades with either a 'hollow ground' geometry or a 'triple chip' blade with the following.

Geometry and Conditions:

| Diada Diamatan | |
|-----------------------|----------------|
| Blade Diameter | 255-305mm |
| Number of Teeth | 80-100 |
| Tooth Thickness | 3-3.5mm |
| Clearance Angle | 15-20° |
| Cutting Angle (Rake) | -5° |
| Angle of Setting Band | 2-3° |
| Blade Speed | 3000-5000rpm |
| Surface Speed | 3000-4000m/min |
| | |

Hole Saws

Hole saws should be sharp, but the pilot drill blunt. It is recommended to drill the hole saw half way through, then turn the Akril over and finish the hole. This prevents the edge from 'blowing out'. De-bur the edge with 100-grit sandpaper.

Determine the position of the outlet on the panel and mark the centre. Now mark 20mm either side of the centre mark. Drill each hole with a 65mm hole saw.

Cutting of Penetrations

When measuring and marking for cut-outs around power outlet boxes etc, ensure enough clearance is given for the switch body and that the cover plates or bulkhead fittings will cover the finished cut-outs.

Use an approved sealer to seal the edge and a 50mm perimeter of the painted side of any Cut Outs.

The Akril logo and Akril trademarks are all the property of CME Coatings, Australia.

DISCLAIMER Akril has produced this catalogue to serve as a general guide for products offered to our clients. We have made every effort to ensure the information contained herein is accurate at time of publication, but accept no responsibility or liability for loss incurred directly or indirectly as a result of the

use of these specifications and technical data. COPYRIGHT The contents of this publication are copyrid reproduction of the material contained herein without the of CME Coatings Pty. Ltd.



Sealing Edges, Perimeters and Cut Outs



It is important to protect the rear (coated) side of Akril from moisture. Akril needs to be sealed with a band of neutral cure silicon extending 50mm from the edge of the panel.

This should include:

- The perimeter of the sheet including any cut outs made
- · Perimeter of any penetrations made i.e. tape holes
- The edges of these cut outs



Installing Akril into a Shower Tray.



water proor board should be laid against framing following manufacturer's instructions, down to within 6mm of shower tray.

Flexible caulking should be installed between top of tray and bottom edge of wall lining in a continuous bead, then smoothed off as illustrated.

Akril is then installed over the wall lining and over the up-stand lip of the tray, as illustrated above with a bead of flexible caulking between; the back of Akril and front of tray up-stand lip, and the top of tray and bottom edge of Akril.

A gap should be left between the two caulking beads to act as a capillary break.

Note: The waterproofing system for your bathroom or shower must meet specific Australia standard building regulations.



Weep Hole Sealing Detail





Note:

Left side Akril piece removed to show detail in more clarity.



Installing an Anti-Fracture Membrane.

Install a suitable anti-fracture membrane in the internal corner running from the finished installed height of the shower, down and over the lip of the tray, terminating at the bottom of the tray lip.

There should be as small a radius as possible in the wall corner.



Pre-drilling Screw Holes (shower frame)



- A minimum of 3 fixing points should be used in a 1.8m high shower.
- A minimum of 4 fixing points should be used in a 2m high shower.



.



STANDARD SHARP DRILL

BLUNT FOR ARKIL





me corner onto the liner at the edge of the anti-fracture membrane.





The internal corner is crucial to the installation as it will allow for thermal expansion and contraction.

Each Akril sheet will expand and contract 3mm into and out of the corner silicone join.

The first sheet will butt into the wall and allow for 3mm expansion while the second sheet will butt onto the first Akril sheet allowing for expansion and contraction against the first Akril sheet which was installed. This will reduce the visible join line to 3mm instead of 6mm.

Hint: Use a straight edge to press Akril onto the wall to ensure a flat finish.



Fixing Shower Frames and Tapes

Tapes

Peel back protective film from front face of Akril, to 25mm beyond the outer edge of the tapes installed perimeter. Apply a bead of flexible caulking around the perimeter and a second bead around the cut out in Akril. Both beads should be finished as shown above to allow for any moisture to drain away. Fix tapes as per manufacturer's instructions.

akril

DOOR RETURN AKRIL SCREWS BITES INTO FRAME ONLY FIBRE CEMENT SHEET FRAMING

Shower Frame

Fit door returns back in place. Fill holes with flexible caulking before screwing returns to the wall. Check for plumb and position before final tightening of door return fastenings.

Sealing the Internal Corner



membrane areas.



Note: Run Silicone down internal corner for water proofing



Note: *The waterproofing system for your bathroom or shower must meet specific Australia standard building regulations.*



Fitting the Showerscreen and Utilities



If the installer is required to fit any extra utilities to the the Akril be sure to follow the steps in this document where machining is needed.

This document is a guideline for installing Akril and will not wear any liability for waterproofing which should be installed to the current Australian Standard.

For technical help please contact Akril on 1800 464 728.

Akril TM ABN 23 007 128 289 15 – 17 Antonella Court Dandenong Victoria 3175 T 1800 464 728 F (03) 9768 3747 www.akril.com.au